

SPECIFICATION SHEET

Updated Apr-2016 www.RubatexUSA.com

Polymer PE Code R56xx

1. DIMENSIONS AND APPEARANCE

Bun size (W x L x T)

Colour

in

48 x 96 x 3

Natural (0), Grey (1), Black (2)

2. PROPERTIES

		R562x	R564x	
Density	pcf	1 - 3	3 - 5	ASTM D3575
	kg/m³	16 - 48	48 - 80	ASTM D3575
Compression deflection (25%)	psi	6	20	ASTM D1056
	kPa	41	138	ASTM D1056
Compression set (50%)	%	30 max.	25 max.	ASTM D1056
Tensile strength	psi	25 min.	100 min.	ASTM D412
_	kPa	172 min.	689 min.	ASTM D412
Elongation	%	50 min.	50 min.	ASTM D412
Water absorption	lbs/sqft	0.01 max.	0.01 max.	ASTM D3575